
## MEISTER

## Product data

## Laminate flooring Meister Design. laminate LS 350



	Tests	DIN/EN	Laminate flooring
		standard	Meister Design. laminate LS 350
General data on pr	oduct composition		
	Type of covering:		Flooring panel with top layer made from specially-resined decor paper
	Total thickness:		approx. 10 mm
	Effective measurement (length × width):		840 × 168 mm
	Product structure:		a. Overlay b. Antistatic decorative paper c. HDF base board (approx. 890 kg/m³ ± 3%) d. Backing
Technical data			
	Locking method:		UniZip
	Wear class:	EN 13 329	23/32
· 12	Electrical behaviour:	EN 1815	In walk-over test according to DIN EN 1815 at climate of $23^{\circ}$ C/25% relative humidity, the personal voltage was Up < 2 kV. The laminate flooring can be described in accordance with EN 14041:2004 as "antistatic floor covering".
	Wear resistance:	EN 13 329 (appendix E)	AC4 (= IP ≥ 4 000 cycles)
ANTI- BACTERIAL SURFACE	Antibactierial surface property:	ISO 22196	Effectiveness of the antibacterial property against Staphylococcus aureus ATCC 6538P and Escherichia coli ATCC 8739: "strong", value of the antibacterial effect $A \ge 3$ .
	Impact resistance (small ball):	EN 17368	≥ 35 mm
	Impact resistance (big ball):	EN 13 329 (appendix C)	≥ 600 mm
	Stain resistance:	EN 438-2	Group 1: grade 5 Group 2: grade 5 Group 3: grade 4-5
	Colour fastness:	EN ISO 4892-2	≥ stage 4 on the grey scale
C <sub>tl</sub> -s1	Fire behaviour:	EN 13 501	Cfl-s1 (hardly flammable)
DS	Slip resistance:	EN 14 041 / 13 893	DS

01/24

	Scratch resistance:	EN 438-2	Grade 4
E1	Formaldehyd Emissions (E1 = 0.1 ppm):	EN 717-1	≤ 0.05 ppm
° DL PCP	Content of Pentachlorophenol:	EN 14 041 / 14 823	< 5 ppm
	Indent after constant load:	EN ISO 24343-1	≤ 0.05 mm
	Castor resistance:	EN ISO 4918	no visible changes or damage with soft, standard castors (type W)
	Behaviour on simulation of shifting furniture foot:	EN ISO 16581	Foot type 0: no visible damage
	Underfloor heating:		Suitable for hot-water underfloor heating Electrical underfloor heating is generally suitable when it is built into the floor screed or the concrete layer and thus does not lie on the concrete layer as foil heating. The heating elements/pipes/wires must lie across the entire area and not just be partly present. If the area is only par tially heated, the floor covering must have expansion joints (system profile strips). The maximum permitted surface temperature is 29° C. Standard foil heating systems are generally not recommended. One exception is self-regulating heating systems which maintain the 29° C surface temperature.
	Underfloor cooling:		A separate leaflet is available for laying on cooled floor constructions.
	Heat transfer resistance:	EN 12 667	0.071 (m <sup>2</sup> K)/W
	Thermal conductivity:	EN 12 667	0.136 W/(m*K)
	Footfall noise reduction:	DIN EN ISO 10140-3	with MEISTER-Silence 15 DB: 16 dB
	Antislip:	DIN EN 16165 (appendix B) / DIN 51130	on request; structure-dependent: - / R 9 / R 10
Tolerances			
	Right-angle of the elements:	EN 13 329	target values met
	Determination of edge straightness:	-	target values met
	Surface flushness:	EN 13 329	target values met
	Joint opening between the elements:	EN 13 329	target values met
General data o	n environment, installation and care		
	Blue Angel:	RAL-UZ 176	awarded
	Disposal:		Residual pieces can be disposed of in household refuse (e.g. thermal treatment) Dispose large quantities according to municipal provisions (e.g. recycling centres) An energetic utilization in authorized plants is recommended.
	Cleaning and care:		Cleaning after completion of construction work/day-to-day cleaning: CC Lamnate Cleaner Special cleaning: CC-Elatex universal stain remover
	Areas of application:		The flooring is suitable for all living areas as well as for commercial areas with normal wear. e. g. offices, waiting rooms, boutiques etc. Special requirements apply to treatment rooms and medical practices.
	AquaSafe-System:		The laminate floor is water-resistant (4 hours protection against standing water) as it has the AquaSafe system's comprehensive protection against humidity. Can be installed in humid rooms like e.g. bathrooms. This does not include outdoor areas and wet rooms, e.g. saunas, shower cubicles, steam rooms and rooms with a floor drain.
	Preconditions for installation:	DIN 18 365	The substrates must be ready for laying on according to the generally recognised rules of the trade, taking into account VOB (German construction contract procedures), part C DIN 18 365 "Floor covering work". The substrate must be dry
			(in the case of mineral substrates max. 2 % or with underfloor heating 1.8 %, with anhydrite screed max. 0.5 % or with underfloor heating 0.3 % residual moisture – measured with CM devices), even, firm and clean. Additionally, any unevenness of 3 mm / per initial metre and 2 mm per further metre must be evened out according to DIN 18 202, table 3, line 4. The installation instructions provided with the product must be observed.















MeisterWerke Schulte GmbH reserves the right to make alterations to material and structures when this serves to improve the quality.

01/24 2/2