



#### PRODUCT DETAILS

<b>Surface treatment</b>	Oil This floor should be oiled immediately after installation.
<b>Dimensions</b>	2419 x 196 x 15 mm
<b>Weight per Package (kg)</b>	22.4 kg
<b>Area per Package (m²)</b>	2.8 m²
<b>Area per pallet (m²)</b>	113.6 m²
<b>Package info</b>	Packages may contain start and stop boards.

#### DETAIL DESCRIPTION

Contains knots and all natural colour variations.

#### COLOUR CHANGE

The colour matures over time

#### FACTS

<b>Design</b>	3-strip
<b>Grading</b>	Dynamic
<b>Range</b>	Kährs Original
<b>Collection</b>	Göteborg Collection
<b>Resandable</b>	2-3 times
<b>Natural/Stained</b>	Stained
<b>Brinell Value</b>	3,7
<b>Joint</b>	Woodloc® 5S
<b>Floor heating</b>	Yes
<b>Warranty</b>	30 years
<b>Wear-layer material</b>	Hardwood
<b>Wear Layer Thickness (mm)</b>	3.5 mm
<b>Core material</b>	Pine/Spruce/Alder
<b>Thickness (mm)</b>	15 mm
<b>Installation method</b>	Floating, Glue-down
<b>Surface Colour</b>	Grey

#### TECHNICAL PROPERTIES

<b>Moisture content</b>	EN13183	7%±2%
<b>Minimum Mean Density kg/m³</b>	>500 kg/m³	
<b>Reaction To Fire</b>	EN13501-1	Dfl-s1
<b>Formaldehyde Emission</b>	EN717-1	E1
<b>Content PCP</b>	CEN/TR14823	≤ 5 x 10-6n
<b>Breaking Strength N/mm²</b>	EN1533	NPD
<b>Thermal Conductivity</b>	EN12664	0,14 W/mK
<b>Thermal Resistance R-Value</b>	.11 (m²K/W)	
<b>Biological Durability</b>	EN350-2	Class 1
<b>CARB2</b>	Compliant	
<b>Slipperiness</b>	CEN/TS15676	NPD

Other products in this collection



Oak Boda



Oak Backa



Oak Vinga



Oak Attebo



Oak Kilesand

CERTIFICATES



Descriptions & Imagery

All samples, images and product description, plus photo and brochure specifications are there for the sole purpose of giving an approximate idea of the items described in them. They shall not form part of the contract or have any contractual force and should be viewed for illustrative purposes only. We cannot guarantee that your computer's display or the quality of the print will accurately reflect the colour of the products. Your product may vary slightly from the images within this literature.